

Properties	ASTM	VisiJet Armor M2G-CL
Composition		
Color		Clear
USP Class VI Certified**		No
Bottle Quantity (kg)		1.5
Density @ 20 °C (solid) (g/cm ³)	D792	
Tensile Strength (MPa)	D638	30-35
Tensile Modulus (MPa)	D638	1500-2000
Elongation at Break	D638	55-65
Flexural Strength (MPa)	D790	40-45
Flexural Modulus (MPa)	D790	1000-1200
Impact Strength (Notched Izod) (J/m)	D256	40-50
Shore A Hardness	2240	N/A
Shore D Hardness	2240	70
Water Absorption (24 hr)	D570	
Heat Distortion Temp @ 0.45 MPa	D648	47 °C
Heat Distortion Temp @ 1.82 MPa	D648	43 °C
Melting Point		NA
Softening Point		NA
Printer Compatibility		ProJet MJP 2500 Plus
Description		Transparent clear

New: VisiJet[®] Armor (M2G-CL)

CLEAR, TOUGH, ABS-LIKE



- For use on:
 - ProJet MJP 2500 Plus
- “Tough” Material
 - Impact-resistant
 - ABS-like snaps & drilling
 - Superior vs. competition for mechanical performance
- World-class clear finish